

443

Golfsmith®

Buffing Compound

Instructions:

Before starting, select the correct buffing compound for the job.

Emery Cake (black): For heavy cutting action for rust and scale removal from cast iron, steel. Best used before White Rouge.

Tripoli (brown): For buffing aluminum, pewter, brass, copper, wood, bone, plastics, (Not for painted surfaces) Best before Pink rouge.

White Rouge: For stainless steel, cast brass, aluminum, chrome and nickel-plated metals and other hard ferrous metals.

Pink Rouge: For bright luster on silver, gold, brass, copper, and other precious metals.

Wheels: The tighter the stitching the more aggressive the cutting.

1. Wash surface to be buffed. Remove dirt, oil, films and dust.
2. Mount buffing wheel on polishing head arbor, chuck adaptor, work arbor or motor shaft.
3. Tighten flange and nut to prevent slipping.
4. "Rake" spinning buffing wheel with sharp tool, such as a screw driver to remove old compounds.
5. Apply new compound to the spinning wheel generously. Using a wiping motion.
6. Buff the item lightly, moving the item on the wheel constantly. Using a wiping motion.
7. Apply compound sparingly but frequently, as needed.
8. Before changing from one compound to another clean wheel by "raking."

When buffing always wear safety glasses or eye shields and dust mask and protective clothing. Hold work firmly and buff below the centerline of the buffing wheel. **DO NOT TAKE YOUR EYES AWAY FROM THE WORK BEING DONE.**

-CAUTION-

Do not ingest; avoid breathing particles; provide adequate ventilation; avoid contact with eyes; wear safety glasses; wear dust mask and protective clothing. Wash compound from skin using soap and water after use. Avoid using around open flames. In case of fire, treat as grease fire.